

SCHEDULE 10 Submittal Data Sheet

SCOPE

Covers ASTM A135/A795 fire protection pipe with nominal wall thickness as shown. Pipe is intended for new construction and retro fit fire sprinkler systems. Pipe is suitable for roll grooving and welding. Fayette's sprinkler pipe is available in beveled or grooved ends and has a rated working pressure of 300PSI. Produced to the latest version of ASTM A135/A795. All products are UL listed and FM approved.

PRODUCT MARKING

Each length of pipe is continuously stenciled to show the manufacturer, type, length and size.

Each bundle of pipe will have a tag securely attached showing quantity, run #, and dimensions.

NPS	OD/in.	ID/in.	Nom. Wall Thickness	Empty Wt. (lbs./ft.)	Water Filled Wt. (lbs./ft.)	C.R.R.*	Pieces per Bundle
1	1.315	1.097	.109	1.410	1.800	15.27	91
1-1/4	1.660	1.442	.109	1.810	2.518	9.91	61
1-1/2	1.900	1.682	.109	2.090	3.053	7.76	61
2	2.375	2.157	.109	2.640	4.223	6.27	37
2-1/2	2.875	2.635	.120	3.530	5.893	4.92	30

DIMENSIONS & WEIGHT

*Calculated using Standard UL CCR formula, UL Fire Protection Diectory, Category VIZY

PRODUCT ASSURANCE

Fayette Pipe Hydro Tests each and every piece of pipe that is produced. We do this to add assurance to the customer that our pipe can be trusted every time it is installed.

- FM Approved
- UL Listed
- Complies with NFPA 13 and 14
- Made from 100% Made and Melted Steel
- NDT Eddy Current Tested
- Hydro Tested



Fayette Pipe applies our Mic Defense coating to all pipe that we manufacture. This coating serves as a protective barrier limiting the opportunity for corrosion from microbiological organisms. The lasting benefits from this coating can be ensured through additional and routine treatment options.



🛠 Fayette Pipe

ASTM A53 Type E Grade A

Submittal Data Sheet

SCOPE

Covers black electric-resistance welded Grade A pipe with nominal wall thickness as shown. Pipe is intended for mechanical and pressure applications and is acceptable for steam, water, gas, or air lines. Pipe is suitable for roll grooving, welding and threading. Produced to the latest revision of ASTM A53A/53M -ASME B36.10M. All products are UL listed and FM approved.

TENSILE REQUIREMENTS

Tensile Strength min.	48000 psi		
Yield Strength min.	30000 psi		
Elongation in 2"	Refer to A53 Table x 4.1		

BEND TEST

For NPS 2" and smaller a length of pipe shall be capable of being bent cold through 90° around a cylindrical mandrel twelve times the size of the outside diameter without developing cracks or opening the weld.

FREQUENCY OF TESTS

Tensile tests are required on 1/500 lengths of pipe for each size.

END FINISH

Plain End:	Mfg. Option
Threaded:	To ANSI Standard B 1.20.1
Coupling:	To ASTM Standard A865



EFENSE ANTIMICROBIAL COATING

Fayette Pipe applies our Mic Defense coating to all pipe that we manufacture. This coating serves as a protective barrier limiting the opportunity for corrosion from microbiological organisms. The lasting benefits from this coating can be ensured through additional and routine treatment options.

CHEMICAL REQUIREMENTS

*Combination of these five elements shall not exceed 1.00%

Carbon	Manganese	Phosphorus	Sulfur	*Copper	*Nickel	*Chromium	*Molybdenum	*Vandium
0.25	0.95	0.05	0.045	0.50	0.40	0.40	0.15	0.08

PERMISSIBLE VARIATIONS IN WALL THICKNESS

Minimum wall thickness at any point shall not be more than 12.5% under nominal wall thickness specified.

PERMISSIBLE VARIATIONS IN OUTSIDE DIAMETER

Pipe shall not vary more than +/- 0.016" from the standard specified.

PERMISSIBLE VARIATIONS IN WEIGHT PER FOOT

Pipe shall not vary more than +/- 10% from the standard specified.

Fayette Pipe

Composition, Max. %

2282 University Drive Lemont Furnace, PA 15456 724.438.7600 sales@fayettepipe.com www.fayettepipe.com





VETERAN OWNED



A DIVISION OF SPECIALTY CONDUIT & MFG.

DIMENSIONS & WEIGHT

NPS	OD/in.	ID/in.	Nom. Wall Thickness	Wt. Ibs./ft.	Pieces per Bundle
1/2	0.840	0.622	0.109	0.85	127
3/4	1.050	0.824	0.113	1.13	91
1	1.315	1.049	0.133	1.68	70
1-1/4	1.660	1.380	0.140	2.27	51
1-1/2	1.900	1.610	0.145	2.72	44
2	2.375	2.067	0.154	3.66	30

PRODUCT MARKING

Each length of pipe is continuously stenciled to show the manufacturer, the grade of pipe (ASTM A53), the kind of pipe (E for Electric Resistance Welded, A for Grade A), and length.

Each bundle of STD A53 will have a tag securely attached showing quantity, run #, and dimensions.


HYDROSTATIC & NONDESTRUCTIVE ELECTRIC TESTING

Hydrostatic inspection test pressures for plain-end pipe are listed in Table X 2.2 of the A53/A53M specification. Test pressures shall be maintained for a minimum of five seconds.

Nondestructive electric testing of the weld seam is performed on all sizes of pipe.



STANDARD SCHEDULE 40 PE/T&C/TBE



NFSA

724.438.7600 sales@fayettepipe.com

A DIVISION OF SPECIALTY CONDUIT & MFG.

APPROVED



ASTM A53 SCH 80 Type E Grade A Submittal Data Sheet

SCOPE

Covers black electric-resistance welded Grade A pipe with nominal wall thickness as shown. Pipe is intended for mechanical and pressure applications and is acceptable for steam, water, gas, or air lines. Pipe is suitable for welding and threading. Produced to the latest revision of ASTM A53A/53M - ASME B36.10M.

TENSILE REQUIREMENTS

Tensile Strength min.	48000 psi		
Yield Strength min.	30000 psi		
Elongation in 2"	Refer to A53 Table x 4.1		

BEND TEST

For NPS 2" and smaller a length of pipe shall be capable of being bent cold through 90° around a cylindrical mandrel twelve times the size of the outside diameter without developing cracks or opening the weld.

FREQUENCY OF TESTS

Tensile tests are required on 1/500 lengths of pipe for each size.

END FINISH

Plain End:	Mfg. Option
Threaded:	To ANSI Standard B 1.20.1
Coupling:	To ASTM Standard A865



EFENSE ANTIMICROBIAL COATING

Fayette Pipe applies our Mic Defense coating to all pipe that we manufacture. This coating serves as a protective barrier limiting the opportunity for corrosion from microbiological organisms. The lasting benefits from this coating can be ensured through additional and routine treatment options.

CHEMICAL REQUIREMENTS

*Combination of these five elements shall not exceed 1.00%

Carbon	Manganese	Phosphorus	Sulfur	*Copper	*Nickel	*Chromium	*Molybdenum	*Vandium
0.25	0.95	0.05	0.045	0.50	0.40	0.40	0.15	0.08

PERMISSIBLE VARIATIONS IN WALL THICKNESS

Minimum wall thickness at any point shall not be more than 12.5% under nominal wall thickness specified.

PERMISSIBLE VARIATIONS IN OUTSIDE DIAMETER

Pipe shall not vary more than +/- 0.016" from the standard specified.

PERMISSIBLE VARIATIONS IN WEIGHT PER FOOT

Pipe shall not vary more than +/- 10% from the standard specified.

Fayette Pipe

Composition, Max. %

2282 University Drive Lemont Furnace, PA 15456 724.438.7600 sales@fayettepipe.com www.fayettepipe.com



DIMENSIONS & WEIGHT

NPS	OD/in.	ID/in.	Nom. Wall Thickness	Wt. Ibs./ft.	Pieces per Bundle
1/2	0.840	0.622	0.147	1.09	91
3/4	1.050	0.824	0.154	1.48	79
1	1.315	1.049	0.179	2.17	44
1-1/4	1.660	1.380	0.191	3.00	34
1-1/2	1.900	1.610	0.200	3.63	29

PRODUCT MARKING

Each length of pipe is continuously stenciled to show the manufacturer, the grade of pipe (ASTM A53), the kind of pipe (E for Electric Resistance Welded, A for Grade A), and length.

Each bundle of XH A53 will have a tag securely attached showing quantity, run #, and dimensions.

HYDROSTATIC & NONDESTRUCTIVE ELECTRIC TESTING

Hydrostatic inspection test pressures for plain-end pipe are listed in Table X 2.2 of the A53/A53M specification. Test pressures shall be maintained for a minimum of five seconds.

Nondestructive electric testing of the weld seam is performed on all sizes of pipe.